



Makrolon® SL sheet

UV resistant sign grade

Makrolon® SL Sign Grade sheet is a polycarbonate product with an advanced UV resistance technology that promotes long lasting outdoor weathering performance. It features outstanding impact strength, excellent dimensional stability, high temperature resistance, and high clarity. This lightweight thermoformable sheet is also easy to fabricate and decorate. Makrolon SL is offered in clear, a wide range of standard sign colors, or can be custom matched to any color. The product, available in either sheet or reels, has a proven track record of outstanding performance in extreme environments and meets the UL 879 standard for electric sign components. A ten (10) year limited product warranty is available for both clear and colors for breakage resistance. Clear sheet is also covered for weathering resistance. The terms of the warranty are available upon request.

Applications

Flat and formed sign faces and channel letters

Regulatory code compliance and certifications

Florida Building Code 2017, 6th Ed.
High Velocity Hurricane Zone
Classified
[Miami-Dade NOA: NOA](#)

UL 879: Electric Sign Components,
UL File #E146154

UL 94: Flammability, UL File #E351891


UL 972: Burglary Resistant Glazing
Materials, UL File #BP2126

Typical Properties

Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D 792	–	1.2
Refractive Index	ASTM D 542	–	1.586
Light Transmission, Clear @ 0.118"	ASTM D 1003	%	86
Light Transmission, B59 White @ 0.118"	ASTM D 1003	%	27
Light Transmission, B54 White @ 0.150" and 0.177"	ASTM D 1003	%	27
Water Absorption, 24 hours	ASTM D 570	%	0.15
Poisson's Ratio	ASTM E 132	–	0.38
MECHANICAL			
Tensile Strength, Ultimate	ASTM D 638	psi	9,500
Tensile Strength, Yield	ASTM D 638	psi	9,000
Tensile Modulus	ASTM D 638	psi	340,000
Elongation	ASTM D 638	%	110
Flexural Strength	ASTM D 790	psi	13,500
Flexural Modulus	ASTM D 790	psi	345,000
Compressive Strength	ASTM D 695	psi	12,500
Compressive Modulus	ASTM D 695	psi	345,000
Izod Impact Strength, Notched @ 0.125"	ASTM D 256	ft-lbs/in	18
Izod Impact Strength, Unnotched @ 0.125"	ASTM D 256	ft-lbs/in	60 (no break)
Instrumented Impact @ 0.125"	ASTM D 3763	ft-lbs	47
Shear Strength, Ultimate	ASTM D 732	psi	10,000
Shear Strength, Yield	ASTM D 732	psi	6,000
Shear Modulus	ASTM D 732	psi	114,000
Rockwell Hardness	ASTM D 785	–	M70 / R118
THERMAL			
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	3.75 x 10 ⁻⁵
Coefficient of Thermal Conductivity	ASTM C 177	BTU-in/hr-ft ² -°F	1.35
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	280
Brittleness Temperature	ASTM D 746	°F	-200
ELECTRICAL			
Dielectric Constant @ 10 Hz	ASTM D 150	–	2.96
Dielectric Constant @ 60 Hz	ASTM D 150	–	3.17
Volume Resistivity	ASTM D 257	Ohm-cm	8.2 x 10 ¹⁶
Dissipation Factor @ 60 Hz	ASTM D 150	–	0.0009
Arc Resistance	–	–	–
Stainless Steel Strip electrode	ASTM D 495	Seconds	10
Tungsten Electrodes	ASTM D 495	Seconds	120
Dielectric Strength, in air @ 0.125"	ASTM D 149	V/mil	380
FLAMMABILITY			
Horizontal Burn, AEB	ASTM D 635	in.	<1
Flame Class @ 0.060"	UL 94	–	HB
Ignition Temperature, Self	ASTM D 1929	°F	1022
Ignition Temperature, Flash	ASTM D 1929	°F	824


Makrolon® SL sheet

Impact Resistance*



*Instrumented Impact per ASTM D 3763, sample thickness 0.125" nominal

UV Weather Resistance



Visible yellowness at 8 or greater

Makrolon® SL Standard Colors

Standard Covestro Color	Standard Industry Color	Standard Gauge
Clear/ A00	–	0.093" - 0.236"
White/ B59	7328	0.093" - 0.118"
White/ B54	7328	0.150" - 0.236"
Red/ D92	6192	0.118" - 0.177"



119 Salisbury Road
 Sheffield, MA 01257
 Toll Free: 800.254.1707
 Fax: 800.457.3553
sfdinfo@covestro.com
sheets.covestro.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

With respect to health, safety and environment precautions, the relevant Safety Data Sheets (SDS) and product labels must be observed prior to working with our products.